

Material Data

Data listed below are only for reference. Data can be adjusted in order to meet special requirement

	NS 25	NS 30	NS 50	NS 65	NS 70
Thickness	0.5mm	1mm	2mm	2mm	2mm
Wavelength	%T	%T	%T	%T	%T
200	0.00	0.00	0.00	0.00	0.00
300	0.00	0.00	0.00	0.00	0.00
360	6.90	6.90	26.90	74.40	50.80
380	11.10	11.10	30.10	85.60	51.40
400	1.45	19.37	48.62	64.71	69.20
410	19.37	19.88	48.58	64.96	68.15
420	20.45	20.72	48.52	65.41	66.20
430	20.72	21.11	49.11	66.14	67.02
440	20.96	21.65	49.30	67.65	67.90
450	21.65	23.15	51.12	67.88	69.22
460	22.13	24.09	52.57	68.24	71.50
470	24.09	24.01	52.22	67.12	71.32
480	23.99	23.92	52.49	67.27	72.10
490	23.92	23.68	52.12	66.97	72.21
500	23.65	23.35	51.90	66.74	72.10
510	23.35	23.44	52.11	68.23	72.46
520	23.41	23.52	52.19	69.03	72.80
530	23.52	23.98	52.65	68.21	72.79
540	23.86	24.38	52.81	67.01	73.10
550	24.38	24.36	52.77	66.34	72.98
560	24.37	24.34	52.72	65.30	72.80
570	24.34	23.33	51.78	65.23	72.66
580	23.51	22.93	51.18	65.16	72.10
590	22.93	22.76	50.77	65.08	71.98
600	22.67	22.27	50.14	64.57	71.50
610	22.27	22.33	50.99	66.12	71.02
620	22.32	22.43	49.83	68.25	70.50
630	22.43	22.19	49.11	70.22	70.02
640	22.11	21.79	48.63	77.31	70.20
650	21.79	21.55	47.98	79.43	69.91
660	21.57	21.26	47.44	84.79	69.80
670	21.26	21.95	47.45	79.12	69.52
680	21.96	22.28	47.44	73.70	69.20
690	22.28	22.98	45.49	75.22	68.92
700	22.86	23.27	47.54	78.30	68.60
720	28.20	28.20	52.20	78.30	67.30
740	26.90	26.90	50.70	82.10	65.50
750	26.30	26.30	49.70	82.10	64.30
760	25.20	25.20	48.50	81.30	62.40
780	23.20	23.20	47.30	81.30	61.10
880	14.90	14.90	35.20	74.70	51.30
920	12.20	12.20	32.00	73.30	48.10
960	10.30	10.30	29.40	72.00	45.30
1000	8.90	8.90	27.50	71.30	43.70
1100	7.60	7.60	25.60	71.30	41.50