

红外玻璃--IS 850

物理化学参数


Nd	ρ (g/cm ³)	Thermal		Chemical	
		Tg(°C)	Ts(°C)	DA	DW
1.52	3.05	559	615	5	4

色度

A[2856K]			D65		
x	y	Y	x	y	Y

光谱要求

Thickness	λ_t (nm)	λ_p (nm)	T λ_p (%)
3mm	850±10	950	>90



The wavelength at T= 45%
 Limit of passband
 Transmittance specified to be λ_p (nm)
*We could get any value of " λ_t " required
 if you could not find the type listed above*

光谱曲线

